
FLUXO 13

Grey Powder for Magnetic Particle Inspection - Dry method

General Appearance & Composition

- Grey powder for MPI - Dry method
- Processing Temperature : 0° C to 300° C
- **FLUXO 13** is a grey magnetic powder.

Approval & Specifications

- NF EN ISO 9934-2
- AMS 3040D
- ASTM E1444-01- Section 5.8
- ASME BOILER AND PRESSURE VESSEL CODE, SECTION V
- ASTM SE-709



Properties

- Performance: 70mm in reference block type 2
- Aspect & color: grey powder
- Particles size: around 75µm
- NOT DANGEROUS

Application

- Remove tinder, rust and other contaminations from surface
- During magnetization spray the powder on the surface
- Defects will appear as grey magnetic particle indications under UV Light

Shelf Life

- Minimum of 5 years, stored at room temperature

Pack Sizes

- Drum 2kg - 20kg (on request)